



LEGACY PREMIUM 6100

PREMIUM REMANUFACTURED INTERIOR LATEX EGGSHELL FINISH

CHARACTERISTICS:

- Remanufactured
- Can be Sprayed or Rolled
- Enhanced Resistance to Dirt
- Great Color Retention
- Excellent Adhesion
- Low Odor
- Soap and Water Cleanup
- Self-Priming Finish Coat for most surfaces (priming with Legacy Restoration primer or equivalent recommended for "difficult to adhere" substrates)

RECYCLED CONTENT:

- Post-Consumer: 50%
- Pre-Consumer: 25%

PHYSICAL PROPERTIES:

- Finish: Eggshell
- Sheen @ 60° - 7-14%

VOLUME SOLIDS:

- Approximately 35%

COLORS:

Available in 12 interior stock colors
Custom colors available upon request

VISCOSITY:

Package Viscosity 100-110 KU

PERFORMANCE

PROPERTIES:

Approximately 200-400 sq. ft. per gallon depending on substrate and application method, porosity and surface texture. Approximate coverage for each coat.

Recommended Dry Film Thickness

- 1.5 to 1.7 Mils DFT

MILDEW RESISTANT:

This coating contains agents that inhibit the growth of mildew on the surface of this coating.

DRYING TIME:

To Touch ---- 30-60 minutes @ 74 degrees F, 30%rH
To Re-coat ----- 3-4 hours
Lower temperatures, humidity, thicker film or improper ventilation will increase these times.

PREPARATION & PRIMING:

BLOCK: (Prime with appropriate primer/filler)
Allow new block to cure before application of primers and finish coats. Remove loose mortar and patch all voids with appropriate patching or caulking material. Clean surface to remove dirt, efflorescence, grease, oil, wax, mildew or other foreign matter.

CONCRETE:

Allow new concrete to cure for 60 days before application of primer and finish coats. Patch all voids with the appropriate patching or caulking material. Power-wash all tilt-up and poured in place concrete to remove any bond-breakers or other construction residue. Clean the surface to remove any dirt, efflorescence, grease, oil, wax, mildew or other foreign material.

METAL:

(Prime with appropriate primer)
Apply finish to primed or previously painted metal with no visible rust. Scrape, power tool clean and sand the surface to remove any dirt, grease, oil, rust, mill scale, loose shop primer or other foreign matter.

STUCCO:

Allow new stucco to cure before application of finish coats. Patch all voids with the appropriate patching or caulking material. Clean the surface to remove any dirt, efflorescence, grease, oil, wax, mildew or other foreign material. Best results are obtained when surface is back-rolled.

WOOD:

(Prime with appropriate primer)
Patch all voids with the appropriate patching or caulking material. Clean the surface to remove any dil1, grease, oil, wax, mildew or other foreign matter.

PREVIOUSLY PAINTED SURFACES:

Patch all voids with the appropriate patching or caulking material. Wash, rinse, scrape, sand and clean the surface to remove any chalk, dirt, grease, oil, wax, mildew, loose paint or other foreign material.

APPLICATION SUBSTRATES:

This product is perfectly suited for recoating over previously painted surfaces without the need for a primer coat. Its premium priming resins provide excellent adhesion and long term performance. It can be applied directly over unprimed drywall in a two coat application.

APPLICATION:

METHODS:

Product may be applied with brush, roller or airless sprayer. Maintain a "wet edge" and apply coating uniformly.

THINNING:

Product intended for use at package Consistency. If thinning is desired, do not thin more than 1/2 pint per gallon.

CLEAN-UP:

Clean up equipment and area with soapy water.

APPLICATION:

Do not apply where material, air or surface Temperature is below 50° F Surfaces and ambient temperatures must be between 48° F and 100° F, 5° above dew point and remain above 48° F for a minimum of four hours after application. All paint products should be tested for adhesion, appearance, color and compatibility prior to application.

PERSONAL:

Paint may be irritating to eyes, nose and skin. Avoid contact with eyes. In case of eye contact, flush at least fifteen minutes and call a physician immediately.

STORAGE:

KEEP FROM FREEZING STORE ABOVE 50° F

MAXIMUM VOC:

**<100 GRAMS PER LITER
<.83 POUNDS PER GALLON**

CAUTION:

Avoid contact with eyes, skin and clothing.

Do not take internally.

Wash thoroughly after handling.

Close container after each use.

For additional safety information consult the Material Safety Data Sheet (MSDS)

KEEP OUT OF REACH OF CHILDREN.

USE ONLY WITH ADEQUATE VENTILATION.